We Will Create a Nice Future Together



NATURE POWER

NP-911B Non-Yellowing Softener for Staple and Bleached Fabrics

PDS

Description

Non-yellowing amino silicone fluid NP-911B has no effect on the degree of whiteness in fabrics. The product imparts a very soft, flexible, and elastic feel to woven and knitted fabrics. Best softening agent for cotton fabrics and cotton blends. Also, NP-911B can be applied to colorful fabrics to make the color brighter.(Not fluorescent brightening agent)

Characteristics

- NP-911B provides soft, smooth and elastic texture on cotton and cotton blend fabrics
- Gives fabrics a wrinkle-free character
- Non-yellowing

Storage & packaging

When stored in its originally sealed packaging at 5°C - 40°C, this product may be stored for up to 8 months from its manufacturing date. Comply with the storage instructions marked on the packaging. Once past this expiration date, TAI COUNTY CHEMICAL no longer guarantees that the product meets the sales specifications. Product comes in 120 kg drums.

Applications

Suitable for staple in "High speed and temperature setting machine". Even in 200°C 150secs, NP-911B still can be nonvellowing.(Increase capacity, but save energy)

Properties

Appearance Transparent to	yellowish liquid
Active ingredient(%)	70.0%
pH(5%Solution,25℃)	6.0 ± 1.5
Ionic type	Slightly Cationic
Diluent	Water

Safetv

This document does not contain the safety information required for the product. Please read the safety data sheet for this product before use.

Processing

To dilute to 10% emulsion (Filter before packaging)

NP-911B	:17 KG
Water	:103 KG
Total	:120 KG

Please filter the dilution by 150 mesh.

Padding process

NP-911B(10%)	:10~30 g/L	
Soaking temperature	:Room temperature	
Setting temperature	:150°C/2.5mins	
(Depending on the actual conditions, you can		
adjust the usage amount.)		

!!This product is sensitive to acid, alkali and hard water. Please test with the own condition before use.!!

TAI COUNTY CHEMICAL

The data provided above is to the best of our knowledge and experience and is without any warranty. Users should thoroughly test any application and independently conclude satisfactory performance before use.

TAIPEI Factory: NO. 91, Museum Rd., Bali Township, Taipei County 24947, Taiwan FACTÓRY REGISTRATION NO: 99.695614.00 YUNLIN Factory: NO. 1, Changqing St., Lunbei Township, Yunlin County 63745, Taiwan FACTORY REGISTRATION NO: 09000892 Tel: 886-2-2610-4457 Fax: 886-2-2610-1363 E-MAIL : service@taicounty.com.tw www.taicounty.com.tw